

Dexnyl© PI-s Polyimide-HT SF Film_52
Technical Data Sheet

No.	Test Item		Typical Value	Inspection reference
1	Appearance		Polyimide film edges neatly without damage, uniform color	Corporation Standard
2	Part no.		PI-s HT 50μm	
3	Thickness		50 ± 10μm	
4	Tensile Strength	MD	≥ 100Mpa	
		TD	≥ 90Mpa	
5	Elongation	MD	≥ 10%	
		TD	≥ 10%	
6	Width		520mm	
7	Length		500m	
8	Surface Resistivity		60 Ω ± 10%	
9	Storage		<p>The film should be stored in a dry and clean room, should be placed in a box with floating support, can not be erected.</p> <p>Not close to the fire, heat or direct sunlight.</p>	

■ The specified values are for indication purpose base on standard testing and does not ensure specific properties, or the suitability for certain application, therefore BIEGLO does not assume any legal responsibility for an improper usage. Status - June 2021