

Celazole® TL-60

Self Lubricating Melt Processable PBI

Typical Properties

PROPERTIES	ASTM METHOD	ENGLISH VALUE	METRIC VALUE
MECHANICAL			
Tensile Strength	D-638	17.4 kpsi	120 MPa
Modulus		2650 kpsi	18,300 MPa
Elongation		0.9%	0.9%
Flexural Strength	D-790	27.6 kpsi	190 MPa
Modulus		2320 kpsi	16,000 MPa
Compressive Strength	D-695	18 kpsi	123 MPa
Modulus		740 kpsi	5100 MPa
TRIBOLOGICAL *			
Wear Rate		0.20 in/1000 hrs	5 mm/1000 hrs
Running Temperature		350°F	177°C
Static Coefficient of Friction		0.30	0.30
Dynamic Coefficient of Friction		0.05	0.05
THERMAL			
Coefficient of Linear Thermal Expansion			
75-300°F	TMA	14 X 10 ⁻⁶ in/in°F	26µm/m°C
Heat Capacity @ 158°F	DSC	0.28 Btu/lb°F	1160 J/kg°C
Heat Deflection Temperature	D-648	590°F	310°C
Temp. of Initial (5%) Weight Loss In:			
Air	TGA	1116°F	602°C
Nitrogen	TGA	1123°F	606°C
Thermal Conductivity @ 70°F	F-433	5.3 Btu in/hr•ft²°F	0.76 W/M°C
OTHER			
Specific Gravity		1.44	1.44
Hardness, Rockwell E	D-785	65	65
Poisson's Ratio		0.42	0.42
Water Absorption	D-570		
24 hours @ 73°F		0.20 %	0.20 %
@ Equilibrium		3.8 %	3.8 %

***Test Conditions**

Mating Material – 1018 Steel
Pressure – 125 psi
Velocity – 800 ft/min
Surface Finish – 16 rms

Distribution by:

BIEGLO GmbH

Bahrenfelder Strasse 242,
22765 Hamburg
+49 40 4011 30000
granules@bieglo.com
www.bieglo.com
www.pbi-shop.de

PBI Performance Products, Inc.
9800 Southern Pine Blvd Suite D
Charlotte, NC 28273 USA
704.554.3378
www.CelazolePBI.com