

Data Sheet

Dexnyl® 2710 PEEK Compound CA30 -26

Test Item	Test Method	Conditions	Units	Test Data
Mechanical Data				
Tensile Strength	ISO 527	Break, 23°C	MPa	250
Tensile Elongation	ISO 527	Break, 23°C	%	1.6
Flexural Strength	ISO 178	Break, 23°C	MPa	370
Flexural Modulus	ISO 178	23°C	GPa	22
Compressive Strength	ISO 604	23°C	MPa	300
Charpy Impact Strength	ISO 179/1eA	Notched	kJ m ⁻²	7
	ISO 179/1U	Unnotched	kJ m ⁻²	45
Izod Impact Strength	ISO 180/A	Notched	kJ m ⁻²	9
	ISO 180/U	Unnotched	kJ m ⁻²	45
Mould Shrinkage	ISO 294-4	Along Flow	%	0.1
		Across Flow	%	0.5
Thermal Data				
Melting Point	ISO 11357	-	°C	343
Glass Transition (Tg)	ISO 11357	Onset	°C	143
Special Heat Capacity	DSC	23°C	kJ kg ⁻¹ °C ⁻¹	1.8
Coefficient of Thermal Expansion	ISO 11359	Along flow below Tg	ppm K ⁻¹	5
		Along flow above Tg	ppm K ⁻¹	6
Heat Deflection Temperature	ISO 75-f	1.8 Mpa	°C	336
Thermal Conductivity	ISO 22007-4	23°C	W m ⁻¹ K ⁻¹	0.95
Flow				
Melt Index	ISO 1133	380°C,5kg	g 10min ⁻¹	5
Miscellaneous				
Density	ISO 1183	Crystalline	g cm ⁻³	1.4
		Amorphous	g cm ⁻³	-
Shore D Hardness	ISO 868	23°C		88
Water Absorption (3.2mm thick Tensile Bar) (by immersion)	ISO 62-1	24h, 23°C	%	0.04
		Equilibrium, 23°C	%	0.3

Distributed by

BIEGLO GmbH
Bahrenfelder Straße 242
22765 Hamburg
+49 40 4011 30000
info@bieglo.com
www.bieglo.com
www.polyimide-shop.de

The specified values are established from average values of several tests and they correspond to our today's knowledge. They are only to be used as information about our products and as help for the material selection. With these values, we do not ensure specific properties, or the suitability for certain application. No warranty, representation, guarantee or legally binding product description is provided by publishing this informational data. For information about divergent properties do not hesitate to contact us. On request we advise you regarding the most appropriate component design and the definition of material specifications more suitable to your application data. Notwithstanding, the customer bears all the responsibility for the thorough examination of suitability, efficiency, efficacy and safety of the chosen products in pharmaceutical applications, medical devices or other end uses. Status: June 2019

Rel. 11/2021