



Data Sheet

Dexnyl® 2710 PEEK Compound CA30 -26

| | | | • | |
|-------------------------------------|-------------|---------------------|--------------------------------------|-----------|
| Test Item | Test Method | Conditions | Units | Test Data |
| Mechanical Data | | | | |
| Tensile Strength | ISO 527 | Break, 23°C | MPa | 250 |
| Tensile Elongation | ISO 527 | Break, 23°C | % | 1.6 |
| Flexural Strength | ISO 178 | Break, 23°C | MPa | 370 |
| Flexural Modulus | ISO 178 | 23°C | GPa | 22 |
| Compressive Strength | ISO 604 | 23°C | MPa | 300 |
| Charpy Impact Strength | ISO 179/1eA | Notched | kJ m ⁻² | 7 |
| | ISO 179/1U | Unnotched | kJ m ⁻² | 45 |
| Izod Impact Strength | ISO 180/A | Notched | kJ m ⁻² | 9 |
| | ISO 180/U | Unnotched | kJ m ⁻² | 45 |
| Mould Shrinkage | ISO 294-4 | Along Flow | % | 0.1 |
| | | Across Flow | % | 0.5 |
| Thermal Data | ISO 11357 | | °C | 343 |
| Melting Point Glass Transition (Tg) | ISO 11357 | Onset | ℃ | 143 |
| Special Heat Capacity | DSC | 23°C | kJ kg ⁻¹ °C ⁻¹ | 1.8 |
| Coefficient of Thermal | ISO 11359 | Along flow below Tg | ppm K ⁻¹ | 5 |
| Expansion Thermal | | Along flow above Tg | ppm K ⁻¹ | 6 |
| Heat Deflection Temperature | ISO 75-f | 1.8 Mpa | °C | 336 |
| Thermal Conductivity | ISO 22007-4 | 23°C | W m ⁻¹ K ⁻¹ | 0.95 |
| Flow | | | | |
| Melt Index | ISO 1133 | 380°C,5kg | g 10min ⁻¹ | 5 |
| Miscellaneous | | | | |
| Density | ISO 1183 | Crystalline | g cm ⁻³ | 1.4 |
| | | Amorphous | g cm ⁻³ | - |
| Shore D Hardness | ISO 868 | 23°C | | 88 |
| Water Absorption (3.2mm | | 24h, 23°C | % | 0.04 |
| thick Tensile Bar) (by immersion) | ISO 62-1 | Equilibrium, 23°C | % | 0.3 |

Distributed by

BIEGLO GmbH

Bahrenfelder Straße 242 22765 Hamburg +49 40 4011 30000 info@bieglo.com www.bieglo.com www.polyimide-shop.de The specified values are established from average values of several tests and they correspond to our today's knowledge. They are only to be used as information about our products and as help for the material selection. With these values, we do not ensure specific properties, or the suitability for certain application. No warranty, representation, guarantee or legally binding product description is provided by publishing this informational data. For information about divergent properties do not hesitate to contact us. On request we advise you regarding the most appropriate component design and the definition of material specifications more suitable to your application data. Notwithstanding, the customer bears all the responsibility for the thorough examination of suitability, efficiency, efficacy and safety of the chosen products in pharmaceutical applications, medical devices or other end uses. Status: June 2019