

GIMIDE™ 7200G-BL

Product Details:

Ultra high-performance thermoplastic polymer, unreinforced, granules suitable for injection molding and stock shapes extrusion, easy flow, black in color.

Application Areas:

Various applications in Automotive, Building and Construction, Consumer, Electrical and Electronics, Hygiene and Healthcare, Industrial, Mass Transportation, and Packaging Industry.

General Properties

Property	Typical Values	Unit	Test Method / Conditions
Density	1.29	g/cc	23°C
% Moisture @150°C/1Hr	0.12	%	GSRF M01
MVR at 360°C/5.0 kg	21	g/10 min	ASTM D 1238

Thermal Properties

Glass Transition Temperature (Tg)	217	°C	ASTM D 3418
Heat Deflection Temperature (HDT)	208	°C	ASTM D 648 /1.8 MPa
Continuous Use Temperature (Expected)	190	°C	UL 746B

Mechanical Properties at 23°C

Tensile Strength	108	MPa	ASTM D 638
Tensile Modulus	4.8	GPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Strength	185	MPa	ASTM D 790
Flexural Modulus	3.8	GPa	ASTM D 790
Izod Impact Strength (Notched)	33	J/m	ASTM D 256
Izod Impact Strength (Un-notched)	880 (NB)	J/m	ASTM D 256

Fire Properties

Flammability	V-0	UL 94/0.8 mm
--------------	-----	--------------

Recommended Processing Conditions

Drying Temperature/Time	4-6 hrs at 150°C
Temperature Settings	350 - 410°C
Nozzle Temperature	345 – 405 °C
Hopper / Throat Temperature	80 – 120°C
Mold Temperature	135 – 180°C

THE INFORMATION PROVIDED IN THIS DATA SHEET CORRESPONDS TO OUR KNOWLEDGE ON THE SUBJECT AT THE DATE OF ITS PUBLICATION. THIS INFORMATION MAY BE SUBJECT TO REVISION AS NEW KNOWLEDGE AND EXPERIENCE BECOMES AVAILABLE. THE DATA PROVIDED FALL WITHIN THE NORMAL RANGE OF PRODUCT PROPERTIES AND RELATE ONLY TO THE SPECIFIC MATERIAL DESIGNATED. THESE DATA MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS, ADDITIVES OR PIGMENTS OR IN ANY PROCESS, UNLESS EXPRESSLY INDICATED OTHERWISE. THE DATA PROVIDED SHOULD NOT BE USED TO ESTABLISH SPECIFICATION LIMITS OR USED ALONE AS THE BASIS OF DESIGN. THEY ARE NOT INTENDED TO SUBSTITUTE FOR ANY TESTING YOU MAY NEED TO CONDUCT TO DETERMINE FOR YOURSELF THE SUITABILITY OF A SPECIFIC MATERIAL FOR YOUR PARTICULAR PURPOSES. SINCE GHARDA PLASTICS CANNOT ANTICIPATE ALL VARIATIONS IN ACTUAL END-USE CONDITIONS GHARDA PLASTICS MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. NOTHING IN THIS PUBLICATION IS TO BE CONSIDERED AS A LICENSE TO OPERATE UNDER OR A RECOMMENDATION TO INFRINGE ANY PATENT RIGHTS. GHARDA PLASTICS ADVISES YOU TO SEEK INDEPENDENT COUNSEL FOR A FREEDOM TO PRACTICE OPINION ON THE INTENDED APPLICATION OR END-USE OF OUR PRODUCTS. FOR FURTHER INFORMATION,